



Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11) **EP 0 637 459 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention  
of the grant of the patent:  
27.09.2000 Bulletin 2000/39

(51) Int. Cl.<sup>7</sup>: **A63B 37/00**

(21) Application number: **94305040.1**

(22) Date of filing: **08.07.1994**

(54) **Golf ball**

Golfbälle  
Balles de golf

(84) Designated Contracting States:  
**DE GB**

(30) Priority: **08.07.1993 JP 19306493**

(43) Date of publication of application:  
**08.02.1995 Bulletin 1995/06**

(73) Proprietor:  
**BRIDGESTONE SPORTS CO., LTD.**  
Chiyoda-ku, Tokyo (JP)

(72) Inventors:  
• Higuchi, Hiroshi  
Yokohama-shi, Kanagawa-ken (JP)  
• Yamagishi, Hisashi  
Yokohama-shi, Kanagawa-ken (JP)  
• Egashira, Yoshinori  
Hidaka-shi, Saitama-ken (JP)  
• Yamada, Tadatoshi  
Mitaka-shi, Tokyo (JP)

(74) Representative:  
**Stoner, Gerard Patrick et al**  
**MEWBURN ELLIS**  
York House  
23 Kingsway  
London WC2B 6HP (GB)

(56) References cited:  
EP-A- 0 264 522      FR-A- 2 666 018  
GB-A- 2 230 531      US-A- 4 625 964  
US-A- 4 650 193      US-A- 4 781 383  
US-A- 4 884 814      US-A- 4 929 678  
US-A- 5 002 281  
  
• DU PONT COMPANY, POLYMER PRODUCTS  
DEPARTMENT, WILMINGTON, DELAWARE  
19898  
• COCHRAN A.J.: 'SCIENCE AND GOLF', 13 July  
1990, E & FN SPON, LONDON \* page 205 - page  
212 \*

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

**EP 0 637 459 B1**

**Description**Prior Art

5 [0001] Golf balls of various structures are currently on the market. Among others, two-piece solid golf balls and thread-wound golf balls share the majority of the market. The two-piece solid golf ball has a rubber based core and an enclosing cover typically of ionomer resin while the thread-wound golf ball is produced by winding thread rubber around a solid or liquid center and enclosing the center in a cover.

10 [0002] Most amateur golfers are fond of two-piece solid golf balls which have excellent flying performance and durability although these balls have the disadvantages of a very hard feel on hitting and low control due to rapid ball separation on hitting. For this reason, many of professional golfers and skilled amateur golfers prefer wound golf balls to two-piece solid golf balls. The wound golf balls are superior in feeling and control, but inferior in flying distance and durability to the two-piece solid golf balls.

15 [0003] Under the present situation that two-piece solid golf balls and wound golf balls have contradictory characteristics as mentioned above, players make a choice of golf balls depending on their own skill and taste.

[0004] In order to develop solid golf balls having a hitting feel approximate to the wound golf balls, two-piece solid golf balls of soft type have been considered. For such two-piece solid golf balls of soft type, soft cores must be used. If the cores are soft, however, repulsion becomes low with a concomitant loss of flying performance and durability is considerably deteriorated. That is, the superior flying performance and durability which are characteristic of two-piece solid

20 [0005] An aim herein is to provide a novel and useful solid golf ball construction. A preferred aim is to achieve a good feel while maintaining the good flying performance and durability which are characteristic of solid golf balls.

25 [0006] In connection with a solid golf ball having a core forming the center and a cover forming the outermost layer, we have found that by providing a soft intermediate layer between the center core and the cover, the center core can be made relatively soft so as to improve feeling without deteriorating flying performance and durability. The hitting feel can be improved in a favourable way.

[0007] We note that US-A-5253871/FR-A-2666018 describes examples of three-piece golf balls having an intermediate layer of amide block polyether. The cover layers on the exemplified balls have hardnesses of 43 to 47 Shore D; the prescribed general range is Shore D 40 to 55 : about 64 to about 80 on the JIS C scale.

[0008] In the present invention the dimensions and densities of these elements are adjusted as follows. An intermediate layer having a thickness of at least 1 mm, a specific gravity of less than 1.2, and a hardness of less than 80 on JIS C scale is formed around a center core having a diameter of at least 26 mm and a specific gravity of less than 1.4 and a cover having a thickness of 1 to 3 mm and a hardness of at least 85 on the JIS C scale is formed on the outer surface of the intermediate layer to complete a solid golf ball. Then even when the center core is softened to a JIS C scale hardness of 80 or less, an excellent feel can be achieved with little or no loss of flying distance and durability. Further, as the intermediate layer is formed of a resin composition based on a thermoplastic polyester elastomer, the hitting feel can be further improved with little or no loss of flying distance and durability.

BRIEF DESCRIPTION OF THE DRAWING

[0009] The only figure, FIG. 1 is a schematic cross section of a three-piece solid golf ball.

EXPLANATIONS: PREFERRED AND OPTIONAL FEATURES

50 [0010] Referring to FIG. 1, there is schematically illustrated a typical three-piece solid golf ball embodying our new concepts. The ball includes a spherical center core 1 forming the center of the ball and a cover 3 forming the outermost layer of the ball. A soft intermediate layer 2 is disposed between the core 1 and the cover 3. The size and specific gravity of the core 1, intermediate layer 2, and cover 3 are in the specific ranges explained below (which may be selected individually, independently of one another).

[0011] The center core generally has a diameter of at least 26 mm, preferably 27 to 37 mm and a specific gravity of less than 1.4, preferably 1 to 1.35. With a diameter of less than 26 mm, feeling is not fully improved by making the center core 1 to be soft and the ball starts to have less elastic repulsion so that the flying distance is reduced. With a specific gravity of 1.4 or more, the ball has a heavier weight which may exceed the weight requirement for golf balls.

[0012] On an impact entailing substantial deformation as found on driver shots, the player gets a feeling which largely depends on the hardness of the center core 1 and varies with the club head speed given by the player. Therefore, the hardness of the center core 1 should be set in accordance with the head speed of the target players. In this

sense, the center core hardness is not particularly limited although it preferably ranges up to 80, more preferably from 40 to 75 on JIS C scale (at the center core surface).

[0013] The center core 1 may be formed from a well-known rubber composition comprising a base rubber, co-crosslinking agent and peroxide through heating, pressing and molding steps. The base rubber may be one conventionally used in solid golf balls and preferably is selected from polybutadiene rubber and mixtures of polybutadiene rubber and polyisoprene rubber. Use of 1,4-polybutadiene rubber containing more than 90% of cis structure is preferred for high repulsion. The co-crosslinking agents used in conventional solid golf balls include zinc and magnesium salts of unsaturated fatty acids such as methacrylic acid and acrylic acid and esters of unsaturated fatty acids such as trimethylpropane trimethacrylate and they may be used. Zinc acrylate is preferred for high repulsion. The co-crosslinking agent is blended in amounts of about 10 to 27 parts by weight per 100 parts by weight of the base rubber. The peroxide may be selected from a variety of peroxides, preferably dicumyl peroxide and mixtures of dicumyl peroxide and 1,1-bis(t-butylperoxy)-3,3,5-trimethylcyclohexane. The peroxide is blended in amounts of about 0.5 to 1 parts by weight per 100 parts by weight of the base rubber. If desired, zinc oxide and barium sulfate may be blended in the rubber composition for specific gravity adjustment while antioxidants may also be blended.

[0014] The intermediate layer 2 has a radial thickness of at least 1 mm, preferably at least 1.3 mm, a specific gravity of less than 1.2, preferably 0.9 to 1.19, and a hardness of less than 80, preferably 45 to 75 on JIS C scale. With a thickness of less than 1 mm, repulsion is lowered to reduce flying distance. With a specific gravity of 1.2 or more, the ball has a heavier weight which exceeds the weight requirement of golf balls. With a JIS C scale hardness of 80 or higher, feeling becomes poor.

[0015] The intermediate layer 2 can be effective in compensating for lower repulsion of the center core 1 which is made soft. It is formed of a soft (JIS C scale hardness < 80), repulsive thermoplastic polyester elastomer.

[0016] The thermoplastic polyester elastomers are polyether ester multi-block copolymers e.g. as may be synthesized from terephthalic acid, 1,4-butane diol, and polytetramethylene glycol (PTMG) or polypropylene glycol (PPG) so that the polybutylene terephthalate (PBT) portion forms hard segments and the polytetramethylene glycol (PTGM) or polypropylene glycol (PPG) forms soft segments. For example, Hytrel® 4047 and G3548W are commercially available from Toray-duPont K.K.

[0017] Examples of the ionomer resin which can be mixed with the thermoplastic elastomer include relatively high repulsion Himilan® 1605 and 1707 commercially available from Mitsui-duPont Polychemical K.K. Usually 0 to 50 parts by weight of the ionomer resin is mixed with 100 parts by weight of the thermoplastic elastomer.

[0018] In addition to the thermoplastic elastomer (and/or ionomer resin) the composition of which the intermediate layer is formed may further contain weight control agents, for example, inorganic fillers such as zinc oxide and barium sulfate, coloring agents such as titanium dioxide, and other additives.

The cover 3 has a radial thickness of 1 to 3 mm, preferably 1.5 to 2.5 mm. A cover of more than 3 mm thick is low in repulsion and feeling whereas a cover of less than 1 mm thick is low in durability such as cut resistance. The hardness of the cover 3 is 85 or higher, more preferably 85 to 100 on JIS C scale. A cover with a hardness of less than 85 would be less repulsive.

[0019] The cover 3 may be formed of an ionomer resin which is conventionally used as the cover of solid golf balls. Exemplary ionomer resins are Himilan® 1706 and 1605 commercially available from Mitsui-duPont Polychemical K.K.

#### 40 EXAMPLE

[0020] Examples of the present invention are given below by way of illustration and not by way of limitation.

#### Examples and Comparative Examples

[0021] Using a center core, intermediate layer, and cover having the composition shown in Table 1, three-piece solid golf balls (Examples 1-7, Comparative Examples 1-2) and two-piece solid golf balls (Comparative Examples 3-4) were prepared which had the parameters and test properties shown in Table 2.

[0022] The center core and the core of the two-piece ball were prepared by kneading the respective components in a roll mill and pressure molding at 155 °C for 15 minutes. The intermediate layer was formed by injection molding so as to enclose the outer surface of the center core. The cover was formed around the intermediate layer or the outer surface of the two-piece ball core by injection molding. The solid golf balls were completed in this way.

[0023] The golf balls were evaluated for flying performance, feeling, and durability by the following tests.

#### 55 Flying performance

[0024] Using a swing robot manufactured by True Temper Co., the ball was hit by a driver at a head speed of 45 m/s and 35 m/s (abbreviated as HS45 and HS35 in Table 2, respectively) to measure the flying distance.

**EP 0 637 459 B1**

Feeling

**[0025]** Professional golfers evaluated a feeling on impact according to the following criterion.

- 5    ○: good  
      Δ: average  
      X: Poor

Durability

10

**[0026]** Using a flywheel hitting machine, the ball was repeatedly hit at a head speed of 38 m/s until the ball was broken. With the number of hits counted, the ball was rated according to the following criterion.

- 15    ○: good  
      Δ: average  
      X: poor

20

25

30

35

40

45

50

55

Table 1

		Example						Comparative Example				
		1	2	3	4	5	6	7	1	2	3	4
5	Center core											
10	Cis-1,4-polybutadiene	100	100	100	100	100	100	100	100	100	100	100
15	Zinc acrylate	25	25	15	25	25	25	25	25	25	15	
	Zinc oxide	52	34	37	26		25	25	75	33	29	
20	Antioxidant	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	
	Dicumyl peroxide	0.65	0.65	0.65	0.65	0.65	0.65	0.65	0.65	0.65	0.65	
25	Intermediate layer											
	Hytrel 4047	100	100	100	100	100		80	100			
30	Hytrel G3548 W						100					
	Himilan 1605							20				
35	Himilan 1650									50		
40	Surlyn 8120									50		
	Cover											
45	Himilan 1706	50	50	50	50	50	50	50	50	50	50	50
	Himilan 1605	50	50	50	50	50	50	50	50	50	50	50
50	Note: The amount of components blended are parts by weight and their proportion is independent among the center core, intermediate layer, and cover.											

Table 2

	Example							Comparative Example			
	1	2	3	4	5	6	7	1	2	3	4
Center core											
Outer diameter, mm	27.68	31.52	31.57	35.24	36.40	31.56	31.56	23.80	31.57	38.58	38.60
Hardness, JIS C	73	73	53	73	73	73	73	73	73	53	81
Specific gravity	1.32	1.25	1.24	1.19	1.03	1.18	1.18	1.46	1.35	1.18	1.16
Intermediate layer											
Thickness, mm	5.3	3.5	3.5	1.8	1.8	3.5	3.4	7.1	3.5		
Hardness, JIS C	61	61	61	61	61	50	68	61	82		
Specific gravity	1.10	1.10	1.10	1.10	1.10	1.18	1.18	1.10	0.97		
Cover											
Thickness, mm	2.2	2.1	2.1	1.9	2.0	2.1	2.2	2.4	2.1	2.0	2.0
Hardness, JIS C	91	91	91	89	91	91	91	91	91	91	89
Specific gravity	0.95	0.95	0.95	0.98	0.95	0.95	0.95	0.95	0.95	0.95	0.98
Performance											
W1 HS45 carry, m	208.0	209.0	209.0	210.5	210.0	209.0	210.0	205.0	209.0	208.0	210.0
total, m	220.5	220.0	221.5	222.5	220.0	221.0	222.0	218.0	221.0	220.0	220.0
W1 HS35 carry, m	141.0	141.0	142.0	141.0	142.0	142.5	141.5	139.0	141.0	141.0	139.5
total, m	147.5	148.0	148.5	148.0	148.5	149.0	148.5	145.0	148.0	148.0	145.5
Feeling	○	○	○	○	○	○	○	○	×	○	×
Durability	○	○	○	○	○	○	○	○	○	×	○

[0027] As is evident from Table 2, the three-piece solid golf balls, and particularly those with the preferred selected dimensions and densities etc. of their components, had a good balance of properties in that the center core can be made soft so as to ensure a pleasant feeling without deteriorating flying performance and durability.

[0028] There has been described a three-piece solid golf ball which includes a core, intermediate layer and cover having controlled size, hardness and specific gravity so that the ball has a good total balance of properties in that a relatively soft center core is used to ensure a pleasant feeling at no sacrifice of flying performance and durability.

5 [0029] Although some preferred embodiments have been described, many modifications and variations may be made thereto in the light of the above teachings. It is therefore to be understood that within the scope of the appended claims, the invention may be practiced otherwise than as specifically described.

#### Claims

- 10 1. A three-piece solid golf ball comprising a centre core (1), an intermediate layer (2) around the core and a cover (3) enclosing the intermediate layer and core;

the centre core (1) having a diameter of at least 26 mm and a specific gravity less than 1.4;  
the intermediate layer (2) being mainly of thermoplastic polyester elastomer, having a thickness of at least 1  
15 mm, a specific gravity less than 1.2 and a hardness less than 80 on the JIS C scale, and  
the cover having a thickness in the range 1 to 3 mm and a hardness of at least 85 on the JIS C scale.

2. A golf ball according to claim 1 wherein the centre core (1) has a hardness of not more than 80 (JIS C).

- 20 3. A golf ball according to claim 2 in which the centre core (1) has a diameter in the range 27 to 37 mm, a specific gravity in the range 1 to 1.35 and hardness in the range 40 to 75 (JIS C);

the intermediate layer (2) is at least 1.3 mm thick, has a specific gravity in the range 0.9 to 1.19 and hardness  
in the range 45 to 75 (JIS C), and  
25 the cover (3) has a thickness in the range 1.5 to 2.5 mm and hardness in the range 85 to 100 (JIS C).

4. A golf ball according to any one of the preceding claims wherein the centre core (1) is of a polybutadiene-based rubber composition.

#### 30 Patentansprüche

1. Dreiteiliger massiver Golfball, umfassend einen zentralen Kern (1), eine Zwischenschicht (2) um den Kern und eine Hülle (3), die die Zwischenschicht und den Kern umschließt;

35 wobei der zentrale Kern (1) einen Durchmesser von zumindest 26 mm und ein spezifisches Gewicht unter 1,4 aufweist;

die Zwischenschicht (2) hauptsächlich aus thermoplastischem Polyesterelastomer besteht, eine Dicke von  
zumindest 1 mm, ein spezifisches Gewicht von weniger als 1,2 und eine Härte unter 80 auf der JIS C-Skala  
40 aufweist, und

die Hülle eine Dicke im Bereich von 1 bis 3 mm und eine Härte von zumindest 85 auf der JIS C-Skala aufweist.

2. Golfball nach Anspruch 1, worin der zentrale Kern (1) eine Härte nicht über 80 (JIS C) aufweist.

3. Golfball nach Anspruch 2, bei dem der zentrale Kern (1) einen Durchmesser im Bereich von 27 bis 37 mm, ein spezifisches Gewicht im Bereich von 1 bis 1,35 und eine Härte im Bereich von 40 bis 75 (JIS C) aufweist;

50 die Zwischenschicht (2) eine Dicke von zumindest 1,3 mm, ein spezifisches Gewicht im Bereich von 0,9 bis 1,19 und eine Härte im Bereich von 45 bis 75 (JIS C) aufweist, und

die Hülle (3) eine Dicke im Bereich von 1,5 bis 2,5 mm und eine Härte im Bereich von 85 bis 100 (JIS C) aufweist.

- 55 4. Golfball nach einem der vorangegangenen Ansprüche, worin der zentrale Kern (1) aus einer Kautschukzusammensetzung auf Polybutadienbasis besteht.

Revendications

1. Balle de golf pleine en trois morceaux, comprenant un noyau central (1), une couche intermédiaire (2) autour du noyau et un couvercle (3) enfermant la couche intermédiaire et le noyau.

5

le noyau central (1) ayant un diamètre d'au moins 26 mm et une densité de moins de 1,4 ;  
la couche intermédiaire (2) étant principalement en un polyester élastomère thermoplastique ayant une épaisseur d'au moins 1 mm, une densité de moins de 1,2 et une dureté de moins de 80 à l'échelle JIS C et  
le recouvrement ayant une épaisseur dans la gamme de 1 à 3 mm et d'une dureté d'au moins 85 à l'échelle JIS C.

10

2. Balle de golf selon la revendication 1, où le noyau central (1) a une dureté de pas plus de 80 (JIS C).

3. Balle de golf selon la revendication 2, dans laquelle le noyau central (1) a un diamètre de l'ordre de 27 à 37 mm, une densité de l'ordre de 1 à 1,35 et une dureté de l'ordre de 40 à 75 (JIS C) ;

15

la couche intermédiaire (2) a au moins 1,3 mm d'épaisseur, a une densité de l'ordre de 0,9 à 1,19 et une dureté de l'ordre 45 à 75 (JIS C), et  
le recouvrement (3) a une épaisseur de l'ordre de 1,5 à 2,5 mm et une dureté de l'ordre de 85 à 100 (JIS C).

20

4. Balle de golf selon l'une quelconque des revendications précédentes où le noyau central (1) est une composition de caoutchouc à base de polybutadiène.

25

30

35

40

45

50

55



**FIG.1**

